

TARGET® TRAFFIC PATCH™

COARSE

May, 2026 Page 1 of 4

PRODUCT

TARGET® TRAFFIC PATCH™ COARSE consists of specially modified Portland cement, finely graded sand and nominal 10-12 mm aggregates, combined in closely controlled proportions to give a rapid setting material for the repair of concrete. The product meets the requirements of ASTM C928 for “Very Rapid Hardening Concrete” repair materials. The rapid strength gain properties are maintained at temperatures even as low as 3 °C (37 °F). The product contains no calcium chloride or other admixtures likely to accelerate the corrosion of reinforcing steel. Product is designed to allow a non-breathable membrane to be placed over top the material, 18 hours after initial set.



The TARGET TRAFFIC PATCH COARSE incorporates fibers and a nominal 10-12 mm coarse aggregate and is intended for use in patches GREATER than 25 mm (1 inch) thick. Alternatively TARGET TRAFFIC PATCH COARSE can be manufactured utilizing no fibers at all (Special order item).

COLOR

Concrete grey

USES

TARGET TRAFFIC PATCH is designed for use as a repair material for cast-in-place or precast concrete where rapid setting and strength gain of the repair are required. Typical applications include patching bridge decks, roads, curbs, sidewalks, parking decks and warehouse floors where the repaired area must be returned to normal service conditions within two hours of placing the repair mix. The material is intended to be used in intense traffic environments or anywhere impact loading will occur. Target Traffic Patch is not designed for use as an overlay material and is intended solely for patching and repair applications. As such, the material should be confined within a designated repair “pocket.”

YIELD

When mixed as directed, each 25 kg (55 lb) bag of TARGET TRAFFIC PATCH will yield approximately 0.43 ft³ (12.1 liters) of repair material. 63 bags per Cubic Yard and 84 bags per Cubic Metre.

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2026 Quikrete International, Inc.



T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D

TARGET® TRAFFIC PATCH™

COARSE

May, 2026 Page 2 of 4

TYPICAL PROPERTIES

When mixed with sufficient water to give a slump of 90 to 100 mm (3 1/2 to 4 inches), TARGET TRAFFIC PATCH COARSE has the following typical properties:

PROPERTY	TYPICAL VALUE	
SETTING TIME , (ASTM C403) minutes Initial at 20 °C (68 °F) Final at 20 °C (68 °F)	25 45	
WORKING TIME , minutes, at 20 °C (68 °F)	20	
AIR CONTENT ,(ASTM C 231) - % Average Volume	5	
COMPRESSIVE STRENGTH (ASTM C39)	MPa	lb/in²
at 1 hour after initial set	14.8	2,150
at 3 hours after mixing	20.7	3,000
at 6 hours	23.8	3,450
at 24 hours	34.5	5,000
at 28 days	51.7	7,500
Scaling Resistance in Presence of Deicing Salt. (ASTM C672) after 50 cycles of freezing and thawing.	No Scaling (Rating 0)	
Bond Strength (ASTM C882)	24 hours – 2.5 Mpa (360 psi) 7 days – 7.7 Mpa (1120 psi)	
Modulus of Elasticity (ASTM C496)	GPa (psi x 10 ⁶) 28 days – 38.5 (5.58)	
Length Change (ASTM C928/ C157)	Wet - % +0.001 Dry - % -0.031	
Resistivity (HAS 1S-05-01)	7 day (ohm-cm) - 2380 28 day (ohm-cm) - 16,500	

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2026 Quikrete International, Inc.



T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D

TARGET® TRAFFIC PATCH™

COARSE

May, 2026 Page 3 of 4

Porosity (ASTM C642)	Absorption, soaked % 5.03
Porosity (ASTM C642)	Absorption, Boiled % 5.18
Unit Mass, SSD, kg/m ³ (pcf)	2,357 (147.1)
Volume permeable voids	11.6
Chloride Content %, Water Soluble (ASTM C1218)	0.011
Sulphate Content, mg/kg dry-wet Water Soluble (AASHTO T290)	2050
Chloride Content, % Acid Soluble (AASHTO T260)	0.016
Freeze Thaw Durability (ASTM C666) – 300 cycles	Durability Factor % 102.7
Visual Assessment	No visible cracks

NOTE:

1. These properties are typical for mixing and initial curing temperatures of 21 °C (70 °F).
2. Compressive strength determined on 100 mm (4 inch) diameter cylinders, moist cured at 23 ± 2 °C (73 ± 3 °F) after 24 hours.

PROCEDURES

1. Remove loose or unsound concrete and other deleterious materials by chipping; saw cutting, scarifying, sandblasting or other mechanical means. A minimum repair thickness of 25 mm (1 inch), with square cut or bell cut edges is preferable. Feather edging is **not** recommended.
2. Remove dust or loose material from the repair area.
3. Saturate the repair area with water, and then allow the concrete to come to a surface-dry condition just before placing the repair mix. **DO NOT** use a Bonding Agent with Target Traffic Patch.
4. Utilize the TARGET TRAFFIC PATCH **COARSE** for repair areas **more** than 25 mm (1 inch) in thickness.
NOTE: TRAFFIC PATCH without fibers can be manufactured on special request.
5. For smaller volume pours of Target Traffic Patch, it is suggested to use a 20 Litre (5 Gallon) pail with a heavy ½” Drill and rectangular “Mud Mixer” Paddle. Add approximately three-quarters of the required water to the bucket or mixer. 1.5 liters (3.3 lb or 1.5 US quarts) of water is usually sufficient at this stage for each 25 kg (55 lb) bag of product. **DO NOT** exceed 3.0 liters (3.2 US quarts) of liquid per 25 kg (55 lb) bag of the Traffic Patch Coarse Mix. Water and mix temperatures, and the temperature of the surface to which the mix is to be applied, should be not less than 3 °C (37 °F) and not more than 30 °C (86 °F). During warm weather the use of iced water can reduce mix temperatures and prevent excessively short setting times.

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2026 Quikrete International, Inc.

T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D



TARGET® TRAFFIC PATCH™

COARSE

May, 2026 Page 4 of 4

During cold weather the use of hot water, and storage of TARGET TRAFFIC PATCH in a warm, dry place before use, will prevent excessively long setting times.

6. Mix until the material has been thoroughly blended and the required consistency has been obtained. A mixing time of 2 minutes is usually adequate.
7. Place the mixed material as rapidly as possible and consolidate well to ensure freedom from voids. Work the mix into the prepared concrete surface to ensure bonding over the full area.
8. If material in the mixer begins to thicken or set, discard the mix. DO NOT add more water.
9. Complete surface finishing operations as quickly as possible. Any conventional concrete finishing techniques may be used.
10. Clean the mixer between batches. Partially set material in the mixer can accelerate the setting of subsequent batches.

CURING

- Under normal conditions moist curing of TARGET TRAFFIC PATCH for 24 hours is desirable, but not essential.
- In hot, dry weather conditions, wet cure for as long as possible.
- Protect from freezing for the first 24 hours, and from temperatures below -3 °C (27 °F) for 72 hours.
- Non-breathable membranes can be applied over top of the material 18 hours after initial set.

CAUTION

- TARGET TRAFFIC PATCH is designed for use only as a patching or filling material.
- In cases where the appropriate grade of TARGET TRAFFIC PATCH for a repair is not clear, contact Target Products Ltd or your TARGET Distributor for advice.

SPECIFICATION GUIDE

Repair concrete shall consist of premixed, dry ingredients produced and packaged in accordance with ASTM Standard C928 for “very rapid hardening” cementitious materials for concrete repairs. When mixed and placed in accordance with the manufacturer's directions, the repair concrete shall develop a compressive strength of not less than 20.7 MPa (3000 psi) after three hours at 21 °C (70 °F).

PACKAGING

TARGET Traffic Patch (fine & coarse) is available in 25 kg (55 lb) bag 56 bags per pallet. Target Traffic Patch can also be packaged in various size Bulk Bags upon request.

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2026 Quikrete International, Inc.

