

1353 - Superstick® SD22011 Dry Process Shotcrete

7 avril 2022

Page 1 of 3

PRODUCT

TARGET® Products Ltd produces a range of bagged dry shotcrete mixes for use in either dry-mix or wet-mix shotcrete processes. Shotcrete aggregates are blended to ACI 506R-90 gradation requirements and shotcretes are available in either ACI Gradation No.2 (medium) or Gradation No.1 (fine) aggregate gradations. Other aggregate gradations can be manufactured on request.

TARGET SUPERSTICK® SHOTCRETE is made with accurately mass-batched blends of Portland cement, silica fume, sand, coarse aggregate and, where required, chemical admixtures, steel fibers or dry-powdered shotcrete accelerators.

All materials used conform to the requirements of relevant standards, including: CSA A23.1-94 "Concrete Materials and Methods of Concrete Construction", ACI 506.2 "Specifications for Materials, Proportioning and Application of Shotcrete", ASTM C1141 "Standard Specification for Admixtures for Shotcrete".

USES

TARGET dry bagged shotcretes are used in a wide range of civil engineering and mining applications. Typical areas of use include:

- Mining applications, including ground support and lining of portals, shafts, drifts, raises, loading pockets, ore passes and underground chambers.
- Ground support and slope stabilization.
- Tunnel and shaft lining.
- Construction of retaining walls.
- Rehabilitation of deteriorated infrastructure, including bridges, dams, sewers, canals and cooling towers.
- Repair of deteriorated marine structures including wharves, jetties, piles and sea walls.
- Repair of deteriorated buildings and structures such as parking structures, grain silos, pulp and paper mills and chemical handling facilities.
- Lining of swimming pools, reservoirs, canals, syphons and pipelines.
- Construction of artificial rockscapes in zoos, aquariums, exhibits and recreational and park facilities.

ADVANTAGES

TARGET SUPERSTICK SHOTCRETE offers many advantages to owners, contractors and engineers, particularly in situations where conventional formed concrete construction would not be appropriate or cost effective. Major advantages of using TARGET SUPERSTICK SHOTCRETE include:

- Supply of a precision mass-batched mixture produced to stringent quality control standards.
- Ease of application, particularly in difficult to access or remote locations.
- Elimination or reduction of formwork.
- Greater thickness of build-up in a single pass relative to conventional shotcrete, particularly in the dry-mix shotcrete process.
- Substantial reductions in rebound, particularly in the dry-mix shotcrete process.
- Reduction in construction time.
- Superior bond to (properly prepared) surfaces.
- Elimination of secondary reinforcing steel or mesh when fiber reinforcement is included in the mixture.
- High early and later age strengths and low permeability.



1353 - Superstick® SD22011 Dry Process Shotcrete

TYPICAL PROPERTIES

TARGET SUPERSTICK SHOTCRETE can be custom formulated to meet specific project requirements for both wet and dry-mix shotcretes. Typical shotcrete performance requirements are given below.

Property	Schedule	Result*
Density [Kg/m ³ (lbs/pi ³)]	-	2278 (142)
Minimal compressive strength [MPa (Psi)] ASTM C 1604	1 day	20.0 (2,900)
	3 days	30.0 (4,351)
	7 days	38.0 (5,511)
	28 days	45.0 (6,526)
Minimal flexural strength [MPa (Psi)] ASTM C 78	7 j days	3.6 (520)
	28 days	4.8 (700)
Hardener air content [%] ASTM C 457	-	5.5
Hardener air void distribution [µm] ASTM C 457	-	229
Cold water absorption [%] ASTM C642	28 days	3.8
Warm water absorption [%] ASTM C642	28 days	4.2
Rapid chlorure permeability [Coulombs] ASTM C 1202	56 days	244 – Very low
Scalling [Kg/m ² (lbs/pi ²)] BNQ 2621-900	56 cycles	≤ 0.50 (0.10)
Freeze / thaw resistance [%] ASTM C 666	300 cycles	96

* All the results are obtained from shotcrete panels, in accordance with the ASTM C 1140 standard. The spraying was carried out by a caster holding an ACI certification (caster for shotcrete, dry spraying process)..

SPECIAL SHOTCRETES

- Fiber reinforced shotcretes can be custom formulated to meet different Toughness Performance Levels using appropriate fiber types and addition rates.
- TARGET Set Accelerator can be added to produce a range of different initial and final setting times and early strength development.
- Air entrainment can be added to wet-mix shotcretes to produce the required parameters of the air void system for freeze-thaw durable shotcrete.
- Special high alumina cement based shotcretes can be formulated for refractory applications and for shotcretes applied to permafrost or frozen ground.

PROCEDURES

TARGET SUPERSTICK SHOTCRETE should be applied in accordance with good shotcrete practice as detailed in ACI 506R "Guide to Shotcrete" and ACI 506.2 "Specifications for Shotcrete". The use of nozzleman qualified to the ACI 506.3R "Guide to Certification of Shotcrete Nozzleman" is strongly recommended.



1353 - Superstick® SD22011 Dry Process Shotcrete

7 avril 2022

Page 3 of 3

CAUTION

- Store bagged shotcrete products in a warm, dry place. Preferably shotcrete temperature at the time of application should be in the range of 10 °C to 20 °C (50 °F to 68 °F). Discard any shotcrete that has been exposed to moisture in the bags and allowed to prehydrate.
- Shotcrete should not be applied to substrates with temperatures below 5 °C (41 °F) unless special cold-weather shotcretes are used.
- Preferably ambient temperatures during shotcrete application should be in the range of 10 °C to 30 °C (50 °F to 86 °F). DO NOT apply shotcrete at temperatures below 5 °C (41 °F) or above 35 °C (95 °F).
- Proper moist curing of applied shotcrete is important to minimize the potential for restrained shrinkage cracking and delamination. Three days of continuous moist curing is the minimum recommended requirement but seven days is preferred.
- In situations where moist curing is not feasible consult Target Products Ltd regarding the use of TARGET Cure and Seal curing compound.

PACKAGING

TARGET SUPERSTICK SHOTCRETE is supplied in 30 kg (66 lb) multiwall paper bags or in synthetic cloth bulk bin bags with up to 1678 kg (3,700 lb) capacity. The bulk bin bags can be supplied with or without discharge spouts. Bags are supplied on pallets and can be capped with plastic sheets and stretch-wrapped for moisture protection. Custom packaging is available on request. Bulk deliveries to silos in the field, or to ready-mix concrete plants can be arranged. Also site production of dry pre-mixed materials, with silo storage, can be provided for large shotcrete projects.

YIELD

Exact yield will depend on the specific shotcrete mix design but for conventional shotcrete mixes the yield and quantity estimating values (excluding an allowance for rebound and wastage) are as follows:

Metre ³	73 bags
Yard ³	56 bags
13,7 liters	Bag of 30 kg
0.48 ft ³	Bag of 30 kg
0.457m ³	Super Bag of 1000 Kg (2204 lb)
0.686 m ³	Super Bag of 1500 Kg (3700 lb)

Product performance is affected by many factors, including storage, application method and conditions, and use. User testing is essential to determine the ability of the product to perform according to the method of application and intended use. No verbal or written information can improve this guarantee and/or replace this guarantee. We will replace the product found to be defective. We cannot be held liable for consequential, indirect or other damages arising from negligence or other circumstances.

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty. Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA. © Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2022 Quikrete International, Inc.

